

PRODUCT DATA SHEET

Sikaplan® WT 5300-13 C

1.3 mm thick FPO sheet waterproofing membrane for pits and ponds

DESCRIPTION

Sikaplan® WT 5300-13 C is a 1.3 mm thick sheet waterproofing membrane. It contains an inlay for restraint and is based on flexible polyolefin (FPO-PP).

USES

Sikaplan® WT 5300-13 C is used for:

- Lining of irrigation ponds
- Lining of artificial lakes and canals
- Lining of leisure ponds and biotopes

Please note:

- The Product is not suitable for permanent exposure to liquids with temperatures above +35 °C.
- The Product is not suitable for potable water storage.

FEATURES

- Proven performance over decades
- High UV stability
- Good resistance to microbial degradation
- High resistance to ageing
- Contains no fungicides, heavy metals, halogens or plasticisers
- Good tensile strength and elongation
- Good resistance to root penetration
- Suitable for contact with acidic (soft) water and alkaline environments
- Good resistance to bitumen
- Can be installed on wet substrates and on compacted soil
- Recyclable through [named] programme

PRODUCT INFORMATION

Composition	FPO/PP	
Packaging	Roll width	2 m
	Roll length	20 m
Refer to the current price list for available packaging variations.		
Colour	Colour	several colours available
Note: The membrane colour might change under the influence of UV light around and above the area of permanent water surface level.		
Shelf life	5 years from date of production	
Storage conditions	The Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Protect the Product from direct weather exposure. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to the packaging.	
Effective thickness	1.30 mm (-0.06 mm / +0.13 mm)	(EN 1849-2)
Mass per area	1.14 kg/m ² (-0.05 kg/m ² / +0.11 kg/m ²)	(EN 1849-2)

Appearance	Surface texture	smooth
------------	-----------------	--------

TECHNICAL INFORMATION

Resistance to static puncture	1.5 kN (- 0.2 kN)	(EN ISO 12236)	
Resistance to root penetration	Pass	(CEN/TS 14416)	
Tensile strength	Longitudinal (MD)	10.0 N/mm ² (- 2.0 N/mm ²)	(EN ISO 527-3)
	Transversal (CMD)	8.0 N/mm ² (- 2.0 N/mm ²)	
	Longitudinal (MD)	≥ 8 N/mm ²	(EN 12311-2)
	Transversal (CMD)	≥ 6 N/mm ²	
Tensile strain at break	Longitudinal (MD)	> 550 %	(EN ISO 527-3)
	Transversal (CMD)	> 550 %	
Joint shear resistance	> 200 N/50mm	(EN 12317-2)	
Foldability at low temperature	No cracks at -40 °C	(EN 495-5)	
Coefficient of thermal expansion	100 × 10 ⁻⁶ K ⁻¹ ± 50 × 10 ⁻⁶ K ⁻¹	(ASTM D696)	
Exposure to bitumen	Bitumen compatibility	Watertight at 60 kPa	(EN 1928; EN 1548)
Resistance to weathering	Aged 3000 h at UV 350 MJ/m ²	> 75 % retained tensile strength and elongation	(EN 12224)
Resistance to oxidation	Change in tensile strength, aged 90 days at +85 °C	< 10 %	(EN 1847; EN 14575)
	Change in elongation, aged 90 days at +85 °C	< 10 %	
Microbiological resistance	Change in tensile strength, aged 16 weeks	< 10 % (MD/CMD)	(EN 12225)
	Change in elongation, aged 16 weeks	< 10 % (MD/CMD)	

SYSTEM INFORMATION

System structure

Ancillary products:

- Sikaplan® WT Fixation Plate PP
- Sikaplan® W Flat Profile Stainless Steel
- Sarnafil® T Prep
- Sarnafil® T Clean

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product

data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

For information on substrate preparation and application, contact Sika Technical Services.

APPLICATION

IMPORTANT

Application by trained personnel

The application of this Product must only be carried out by an applicator that is trained or approved by Sika. The applicator must also be experienced in this type of application.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Egypt

1st Industrial Zone (A)
Section #10, Block 13035
El Obour City, Egypt
TEL: +202 44810580
FAX: +202 44810459
egy.sika.com



Product Data Sheet

Sikoplan® WT 5300-13 C
January 2025, Version 04.01
020720201500000006

SikoplanWT5300-13C-en-EG-(01-2025)-4-1.pdf