

Method Statement for Application “SIKA EGYPT”

Sikadur -PF

Scope: Epoxy Resin Paste (Solvent free, two component, adhesive and fine pore sealing and smoothing repair putty).

Preliminary Works and surface preparation

- 1.1 Clean out surfaces, using small wire brushes or compressed air to remove all loose and friable materials, as well as mud and other impurities.
- 1.2 All concrete surfaces must be clean, free from standing water and all loosely adhering particles. Concrete must be full cured at least 3 - 4 week old, depending on climate.

2. Execution

o Mixing and Application

- 2.1 Mix the resin material Sikadur -PF according the instruction to use (see data-sheet) recommended mechanical mixing with electrical stirrer (300-600 rpm) and using the correct sika mixing paddle (disc type) and apply only while the material is in its Pot life time (approx. 40 minutes at 30 Deg. Celsius).

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request



2.2 After mixing apply directly to the prepared substrate by trowel or spatula.
On damp surfaces, ensure that it is well rubbed in.

2.3 Maximum layer thickness is 3 mm.



Construction

*For any further clarification don't hesitate to contact Sika Egypt
Technical Department.*

**Sika Egypt
Technical Department**



Sika Egypt El Abour City 1st industrial zone (A) Section # 10 Block 13035,
Phone: +2 02 46100714 / Fax: +2 02 46100759
Mobil : 0123271730