

PRODUCT DATA SHEET

Sika® Permacor®-1705

SOLVENT CONTAINING 1-PACK ZINC-PHOSPHATE PRIMER FOR STEEL

DESCRIPTION

Sika® Permacor®-1705 is a solvent-borne 1-pack primer based on alkyd resin.

USES

Sika® Permacor®-1705 may only be used by experienced professionals.

Sika® Permacor®-1705 is used as an anti-corrosive primer for atmospheric exposed steel surfaces.

CHARACTERISTICS / ADVANTAGES

- Fast drying, universally applicable as primer with a great range of dry film thicknesses

APPROVALS / CERTIFICATES

- Tested and official approved primer for Sika® Unitherm® and Sika® Pyroplast® fire protection systems on steel.

PRODUCT INFORMATION

Packaging	Sika® Permacor®-1705	25 kg net., 3 l
	Sika® Thinner S	25 l, 10 l and 3 l
Appearance / Colour	Red brown approx. RAL 8012	
Shelf life	Min. 2 years	
Storage conditions	In originally sealed containers in a cool and dry environment.	
Density	~1.4 kg/l	
Solid content	~49 % by volume ~67 % by weight	

TECHNICAL INFORMATION

Chemical Resistance	Resistant to weathering.
Temperature Resistance	Dry heat up to + 80°C

SYSTEMS

Systems

Primer for steel:
1 x Sika® Permacor®-1705

Suitable top coatings:
Versatile overcoatable with 1-pack top coats and with Sika® Unitherm® and Sika® Pyroplast® systems for steel.

APPLICATION INFORMATION

Thinner

Sika® Thinner S
If necessary max. 3 % Sika® Thinner S may be added to adapt the viscosity.

Consumption

Theoretical material-consumption/VOC without loss for medium dry film thickness:

Dry film thickness	40 µm	80 µm
Wet film thickness	85 µm	165 µm
Consumption	~0.114 kg/m ²	~0.229 kg/m ²
VOC	~37.7 g/m ²	~75.6 g/m ²

Product Temperature

Min. + 5°C

Relative Air Humidity

Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point.

Surface Temperature

Min. + 5°C

Waiting Time / Overcoating

At + 20°C Min. 16 h

Drying time

Drying time at + 20°C

Loadable after ~16 h

Final drying time

Depending on film thickness and temperature full hardness is achieved within 1 week.

APPLICATION INSTRUCTIONS

method will provide the requested results.

SUBSTRATE PREPARATION

SURFACE PREPARATION

Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944, part 4.
Free from dirt, oil and grease.

MIXING

Sika® Permacor®-1705 is supplied ready for use.
Stir thoroughly prior to application.

APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application

By brush and roller

Conventional high pressure spraying:

- Nozzle size 1.3 - 2.0 mm
- Pressure 4 - 6 bar

Airless-spraying:

- Pressure min. 150 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)
- Spraying angle 40° - 80°

CLEANING OF EQUIPMENT

Sika® Thinner S

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

Information on the safe handling of chemical products, as well as the essential physical, safety-related, toxicological and ecological data can be found in the current safety data sheets. Observe all relevant regulations, e.g. the hazardous substances act. Further notes and information data sheets on product safety and disposal can be found on the Internet at www.sika.de.

DIRECTIVE 2004/42/CE LIMITATION OF EMISSIONS OF VOC

For product category IIA / i, Type SB, the maximum permissible content of VOC as per directive 2004/42/CE is 500 g/l (limit 2010).

The maximum content of Sika® Permacor®-1705 remains below 500 g/l VOC.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Egypt

1st Industrial Zone (A)
Section #10, Block 13035
El Obour City, Egypt
TEL: +202 44810580
FAX: +202 44810459
egy.sika.com

Product Data Sheet
Sika® Permacor®-1705
August 2016, Version 01.01
020601000240000009

SikaPermacor-1705-en-EG-(08-2016)-1-1.pdf

