


SikaWrap®-103 C

Woven carbon fiber fabric for structural strengthening

Product Description

SikaWrap®-103 C is a unidirectional woven carbon fiber fabric for the wet application process.



Uses

Strengthening of reinforced concrete structures, brickwork and timber to increase flexural and shear load capacity. Reasons:

- Prevention of defects caused by seismic action
- Blast mitigation (accidents or terrorism)
- Improved seismic performance of masonry walls
- Substitute missing rebars
- Strength and ductility of columns
- Increasing loading capacity of structural elements
- Change of building utilisation
- Structural design construction defects
- Improved serviceability
- Structural upgrading to comply with current standards

Characteristics / Advantages

- Manufactured with weft fibers to keep the fabric stable (heat-set process)
- Multifunctional use for every kind of strengthening requirement
- Flexibility of surface geometry (Beams, columns, chimneys, piles, walls, silos)
- Approvals available in several countries
- Low density for minimal additional weight
- Economical compared to traditional techniques

Tests

Approval / Standards

Conforms to the requirement of:
- ICBO Evaluation Report ER 5558 (USA).

Product Data

Form

Fiber Type

Mid strength carbon fibers.

Fabric Construction

Fiber orientation: 0° (unidirectional).

Warp: black carbon fibers (99% of total areal weight).

Weft: white thermoplastic heat-set fibers (1% of total areal weight).



Packaging		
	Fabric length / roll	Fabric width
1 roll in cardboard box	≥ 50 m	600 mm
Storage		
Storage Conditions / Shelf Life	24 months from date of production if stored properly in undamaged original sealed packaging in dry conditions at temperatures between +5°C and +35°C. Protect from direct sunlight.	
Technical Data		
Areal Weight	610 g/m ² ± 20 g/m ²	
Fabric Design Thickness	0.337 mm (based on fiber content)	
Fiber Density	1.79 g/cm ³	
Mechanical / Physical Properties		
Dry Fiber Properties	Tensile strength: 3'900 N/mm ² (nominal) Tensile E-modulus: 230'000 N/mm ² Elongation at break: 1.5% (nominal)	
Laminate Properties	Laminate thickness: 1.4 mm per layer (impregnated with Sikadur [®] -300). Ultimate load: 1000 kN/m width per layer (at typical laminate thickness of 1.4 mm). Tensile E-modulus: 48.0 kN/mm ² (based on typical laminate thickness of 1.4 mm). Note: The above values are typical and indicative only. The achievable laminate properties obtained from tensile test are dependant on the impregnating/laminating resin used and the type of tensile testing procedure. Apply material reduction factors according to the relevant design standard.	
Design	Design strain: This value is dependent on the type of loading and must be adapted according to the relevant design standards.	
System Information		
System Structure	The system configuration as described must be fully complied with and may not be changed. Concrete primer - Sikadur [®] -330 / Sikadur [®] -300. Impregnating / laminating resin - Sikadur [®] -300. Structural strengthening fabric - SikaWrap [®] -103 C. For detailed resin properties, fabric application details and general information, refer to Sikadur [®] -300 Product Data Sheet.	
Application Details		
Consumption	Primer on prepared substrate (depending on the roughness): - Smooth surface: ~ 0.5 kg/m ² (Sikadur [®] -300 or Sikadur [®] -330). - Rough surface: ~ 0.5 - 1.0 kg/m ² (Sikadur [®] -330 or Sikadur [®] -300 mixed with max. 5% thixotropic agent Sikadur [®] -513). Impregnation resin for every layer (manually or with saturator): - ≥ 0.75 kg/m ² (Sikadur [®] -300).	
Substrate Quality	Specific requirements: Minimal substrate tensile strength: 1.0 N/mm ² or as specified in the strengthening design.	

Application Instructions

Application Method / Tools

The fabric can be cut with special scissors or razor knife. Never fold the fabric!
Refer to Sikadur[®]-300 Product Data Sheet for impregnating / laminating procedure.

Notes on Application / Limitations

This product may only be used by experienced professionals.

Minimum radius required for application around corners: > 20 mm.
Grinding edges or building up with Sikadur[®] mortars may be necessary.

In fiber direction, overlapping of the fabric must be at least 100 mm depending on SikaWrap[®] type or as specified in the strengthening design.

For side-by-side application, no overlapping length in the weft direction is required. Overlaps of additional layers must be distributed over the column circumference.

The strengthening application is inherently structural and great care must be taken when choosing suitably experienced contractors.

The SikaWrap[®]-103 C fabric is coated to ensure maximum bond and durability with the Sikadur[®] impregnating/laminating resins. To maintain system compatibility do not interchange system parts.

The SikaWrap[®]-103 C may be / must be coated with a cementitious overlay or coatings for aesthetic and / or protective purposes. Selection will be dependent on exposure requirements. For basic UV protection use Sikagard[®]-550 W Elastic, Sikagard[®] ElastoColor-675 W or Sikagard[®]-680 S.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

