

Method Statement for Application “SIKA EGYPT”

Sikanol[®] -M

1 Scope: Normal Setting Air Entraining /Mortar Plasticizer.

Preliminary Works and surface preparation

- 1.1 Clean out surfaces, using small wire brushes or compressed air to remove all loose and friable materials, as well as mud and other impurities.
- 1.2 All concrete surfaces must be clean, free from standing, water and all loosely adhering particles.

2. Execution

- Mixing and Application

Always keep the water/cement ratio to a minimum to enable correct working and compaction. A W/C of less than 0.4 is advised. **Sikanol M** is added to the clean mixing water prior to its addition to the dry mixed cement: sand. The consumption is 0.1 – 0.2% by weight of cement.

For any further clarification don't hesitate to contact Sika Egypt Technical Department.

Sika Egypt Technical Department

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request

