

## PRODUCT DATA SHEET

# Sika® Plastiment® RB 3030

(formerly MasterRheobuild® 3030)

High range, water-reducing superplasticiser for rheoplastic concretes

### DESCRIPTION

Sika® Plastiment® RB 3030 is formulated from synthetic polymers specially designed to impart rheoplastic qualities to concrete.

A rheoplastic concrete is a fluid concrete, easily flowing, but at the same time free from segregation and bleeding having the same w/c ratio as that of a low slump concrete without admixture with a slight set retarding effect. Also, it provides a substantial water reduction effect for promoting high, early and ultimate strengths.

Sika® Plastiment® RB 3030 is chloride-free.

### USES

Sika® Plastiment® RB 3030 considerably improves the properties of fresh and hardened concrete.

- Microsilica concrete
- Mass concrete pours
- Ready-mixed concrete
- Long distance transport
- Pumped concrete
- Casting in hot climates

### PRODUCT INFORMATION

<b>Packaging</b>	1000 lt. flow bins. Bulk supply in tanker trucks is available upon request
<b>Shelf life</b>	Up to 12 months if stored according to manufacturer's instructions in unopened containers.
<b>Storage conditions</b>	Sika® Plastiment® RB 3030 must be stored where temperatures do not drop below +5 °C. If product has frozen, thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.
<b>Appearance and colour</b>	Dark brown liquid

### FEATURES

- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability

### CERTIFICATES AND TEST REPORTS

ASTM C-494: Types D and G  
BS 5075: Part 3

Density	1.130-1.160
pH-Value	5-7
Total chloride ion content	Nil to BS 5075

## APPLICATION INFORMATION

<b>Recommended dosage</b>	Optimum dosage of Sika® Plastiment® RB 3030 should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial: in normal concrete, a dosage of between 0.6 - 2.0 ltr/100kg of cement.
<b>Dispensing</b>	Sika® Plastiment® RB 3030 is a ready-to-use liquid, which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the concrete after 50 to 70% of the mixing water has been added. Automatic dispensers are available.
<b>Compatibility</b>	Sika® Plastiment® RB 3030 is compatible with all cements and most air-entraining agents meeting ASTM standards. The addition of Sika® Plastiment® RB 3030 and SikaControl®-111 AER (air-entraining agent) to concrete is recommended where it is required to withstand freezing and thawing cycles.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### Sika Egypt

1st Industrial Zone (A)  
Section #10, Block 13035  
El Obour City, Egypt  
TEL: +202 44810580  
FAX: +202 44810459  
egy.sika.com



### Product Data Sheet

Sika® Plastiment® RB 3030  
May 2024, Version 01.01  
02130300000002197

SikaPlastimentRB3030-en-EG-(05-2024)-1-1.pdf