

PRODUCT DATA SHEET

Sikament® RB 890

(formerly MasterRheobuild® 890)

High range, water-reducing superplasticiser for rheoplastic concretes

DESCRIPTION

Sikament® RB 890 is formulated from synthetic polymers specially designed to impart rheoplastic qualities to concrete.

A rheoplastic concrete is a fluid concrete with a slump of at least 200mm, easily flowing, but at the same time free from segregation and having the same w/c ratio as that of a low slump concrete (25mm) without admixture.

USES

Sikament® RB 890 considerably improves the properties of fresh and hardened concrete.

- Microsilica concrete
- Mass concrete pours
- Ready-mixed concrete
- Long-distance transport
- Pumped concrete
- Casting in hot climates

PRODUCT INFORMATION

Packaging	1000 lt. flow bins. Bulk supply in tanker trucks is available upon request
Shelf life	Up to 12 months if stored according to manufacturer's instructions in unopened containers.
Storage conditions	Store in dry conditions and at temperatures between +5°C and +35°C. Protect from direct sunlight and frost. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging
Appearance and colour	Dark brown liquid
Density	1.200-1.250 kg/l at 25°C

FEATURES

- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability

CERTIFICATES AND TEST REPORTS

ASTM C-494 Type B, D and G

Recommended dosage

Optimum dosage of Sikament® RB 890 should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial: in normal concrete, a dosage of between 0.8-2ltr/100kg of cement; in high performance microsilica concrete, a dosage of between 1.5-3ltr/100kg of cement. Dependent upon mix requirement, it is possible to use a higher dosage of Sikament® RB 890 without causing any adverse effects upon the concrete. Please consult Master Builders Solutions' Technical Services Department for further information.

Dispensing

Sikament® RB 890 is a ready-to-use liquid, which is dispensed into the concrete together with mixing water. The plasticising effect, or water reduction, is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of Sikament® RB 890 to dry aggregate or cement is not recommended. Automatic dispensers are available.

Compatibility

Sikament® RB 890 is compatible with all cements and most air-entraining agents meeting the ASTM standards. The addition of Sikament® RB 890 and SikaControl®-111 AER (air-entraining agent) to concrete is recommended where it is required to withstand freezing and thawing cycles.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Field service, where provided, does not constitute supervisory responsibility. For additional information, contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

ECOLOGY, HEALTH AND SAFETY

Sikament® RB 890 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information, refer to the material safety data sheet.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Egypt

1st Industrial Zone (A)
Section #10, Block 13035
El Obour City, Egypt
TEL: +202 44810580
FAX: +202 44810459
egy.sika.com

**Product Data Sheet**

Sikament® RB 890
March 2024, Version 01.01
02130200000002198

SikamentRB890-en-EG-(03-2024)-1-1.pdf