

PRODUCT DATA SHEET

SikaEmaco[®] S 488

(formerly MEmaco S 488)

Thixotropic, shrinkage compensated, structural concrete repair mortar for hand and spray application

DESCRIPTION

SikaEmaco[®] S 488 is a single component, high strength, high modulus, shrinkage compensated structural repair mortar that meets the requirements of EN 1504-3 class R4. Mixed with water it forms a thixotropic mortar that can be easily applied by trowel or spray.

USES

SikaEmaco[®] S 488 is used for the structural repair of concrete elements such as:

- Columns, piers and cross beams of bridges
- Cooling towers and chimneys and other industrial environments
- Water treatment and sewerage facilities before subsequent coating
- Tunnels, pipes, outfalls and all below ground construction
- Marine structures

FEATURES

- Easy-to-use product, only mix with water.
- Thixotropic mortar, application without extra bonding primer.
- Very good workability, can be easily spray- or trowel-applied.
- Can be applied inside and outside, on horizontal, vertical and overhead surfaces.
- Shrinkage-compensated mortar to reduce the risk of shrinkage cracking both in the fresh and in the hardened state under dynamic load.
- High carbonation resistance.
- High resistance against freeze/thaw and de-icing salts.

PRODUCT INFORMATION

Packaging	SikaEmaco [®] S 488 is available in 25 kg paper bags. Larger packaging (Big bags) available on request in several locations. Please check with your local Sika contact.
Shelf life	6 months if stored at below mentioned storage conditions.
Storage conditions	Store at ambient temperatures, out of direct sunlight, in cool, dry warehouse conditions and clear of the ground on pallets protected from rainfall prior to application.
Appearance and colour	Grey Powder
Maximum grain size	2 mm
Soluble chloride ion content	≤ 0.05 % (EN 1015-17)

TECHNICAL INFORMATION

Compressive strength	1 day (at 21±2 °C)	≥ 17 MPa	(EN 12190)
	7 days (at 21±2 °C)	≥ 30 MPa	
	28 days (at 21±2 °C)	≥ 50 MPa	
Modulus of elasticity in compression	≥ 25,000 N/mm ²		(EN 13412)
Flexural-strength	28 days (at 21±2 °C)	≥ 7 N/mm ²	(EN 196-1)
Pull-out resistance	Adhesion to Concrete after 28 days	≥ 2.0 MPa	(EN 1542)
Capillary absorption	≤ 0.5 kg·m ⁻² ·h ^{-0.5}		(EN 13057)
Freeze thaw de-icing salt resistance	Adhesion to Concrete after Freeze-Thaw (50 cycles with salt)	≥ 2.0 MPa	(EN 13687-1)
Carbonation resistance	dk ≤ Reference Concrete		(EN 13295)
Reaction to fire	Class A1		(EN 13501-1)

APPLICATION INFORMATION

Fresh mortar density	approx. 2.0 to 2.1 g/cm ³
Consumption	Approx. 1,850 kg powder is needed to prepare 1 m ³ of fresh mortar. A 25 kg bag will yield approx. 13 to 13.5 l of mortar.
Layer thickness	From 6 to 40 mm in one layer.
Material temperature	+5 to +30 °C
Ambient air temperature	+5 to +35 °C
Mixing ratio	3.5 to 4.0 l water per 25kg bag
Substrate temperature	+5 to +35 °C
Pot Life	Approx. 45 to 60 minutes (at 21±2°C and 60±10% relative humidity). Higher temperatures will reduce these times and lower temperatures will extend them.
Curing rate	Full cure of material is reached after 28 days (at 21±2 °C).

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Only mix complete, undamaged bags of SikaEmaco® S 488.
- Do not apply SikaEmaco® S 488 at temperatures below +5 °C nor above +35 °C
- Do not apply SikaEmaco® S 488 in case of strong winds.
- Do not add cement, sand or other substances to SikaEmaco® S 488 mixes.
- Never add water or fresh mortar to a mortar mix which has already begun to set.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Concrete must be fully cured, clean and sound to ensure good adhesion. All loose traces of concrete or mortar, dust, grease, oil, etc. must be removed. SikaEmaco® S 488 needs a rough surface to bind to. Non-impact/vibrating cleaning methods, e.g. shot blasting, sandblasting or high-pressure water jetting are recommended to prepare and roughen the surface. Aggregate should be clearly visible on the surface of the concrete structure after surface preparation. Make surface rough, using a chisel or scarifier. Cleaning methods, e.g. grit or high water pressure blasting are recommended. Aggregate should be clearly visible on the surface of the concrete structure after surface preparation. The prepared concrete must have a minimum direct tensile strength of 1.5 N/mm². Cut the edges of the repair vertically to a minimum depth of 6 mm.

The prepared substrate should be completely pre-soaked for preferably 12, but least 2 hours before applying SikaEmaco® S 488. The surface must be mat-damp, but without standing water.

If reinforcing steel is visible, clean to a minimum grade of Sa 2 according to ISO 8501-1 / ISO 12944-4. Sandblasting of reinforcement is recommended. In case of chloride contamination of the concrete or when depth of cover is less than 10 mm, the reinforcement must be protected by using protective primers like e.g. SikaEmaco P 5000 AP.

MIXING

Open the bags a short time before the mixing is started. Damaged or opened sacks should not be used. Pour the minimum amount of mixing water 3.5 l per 25 kg bag into the forced action mixer. Use clean tap water only!

Start the mixer and add SikaEmaco® S 488 rapidly and continuously. Mix for about 3 minutes until the mortar has a uniform and lump-free consistency. Add water if necessary within the allowed mixing ratio until required consistency is achieved and mix again about 2 minutes.

The water content can slightly vary depending on ambient temperature and relative humidity.

Small mortar quantities can be mixed with a suitable paddle attached to a powerful, slow speed electric drill (max. 500 rpm).

APPLICATION

Hand Application:

Before SikaEmaco® S 488 is applied to the final layer thickness, we advise to apply a thin scrape coat of mixed mortar or a bonding slurry mixed of SikaEmaco® S 488 mortar (with a bit more water) onto the prepared damp substrate. Then apply the mixed SikaEmaco® S 488 mortar wet-in-wet using a screeding beam, trowel or wooden board to the desired thickness between 6 to max. 40 mm.

Spray Application:

First spray-apply a thin contact layer onto the prepared damp substrate, then apply multiple layers of SikaEmaco® S 488 until the required layer thickness of max. 40 mm is obtained. Spraying with the necessary pressure will improve the adhesion of SikaEmaco® S 488.

Finishing:

Smoothing with a trowel or finishing by wood or steel float can be done as soon as the mortar has begun to stiffen (usually after 60 to 90 minutes at 21±2 °C and 60±10 % rel. humidity). At lower temperatures and/or higher humidity these times will be extended; at higher temperatures and/or lower humidity these times will be shortened.

CURING TREATMENT

Immediately after the SikaEmaco® S 488 surface is finally finished, cover all exposed mortar with clean wet hessian and keep moist by covering with polythene between 1 to 7 days depending on the weather conditions.

CLEANING OF EQUIPMENT

Tools and mixer must be cleaned immediately after use with water. Cured material can only be removed mechanically.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and reg-

ulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Egypt

1st Industrial Zone (A)
Section #10, Block 13035
El Obour City, Egypt
TEL: +202 44810580
FAX: +202 44810459
egy.sika.com



SikaEmacoS488-en-EG-(09-2024)-3-1.pdf

Product Data Sheet

SikaEmaco® S 488
September 2024, Version 03.01
02030200000002182

