

## PRODUCT DATA SHEET

# SikaShield® P25 S EG 3 mm

### PLASTOMERIC MODIFIED BITUMINOUS WATERPROOFING MEMBRANE

#### DESCRIPTION

SikaShield® P25 S EG 3 mm Sand is an APP modified, bituminous, torch-applied, waterproofing membrane. It is reinforced with a dimensionally stable non-woven polyester inlay. The underside has a thin polyethylene burn-off film for easy application.

It can be applied to wood, metal and concrete substrates including over existing bitumen roofing membranes.

Top surface finish: sand.

Thickness: ~3,0 mm

#### USES

Waterproofing membrane for:

- Damp proofing of the exterior walls of basements against percolating water and damp soil
- Flat roofs under protective layers or ballast
- Balconies and terraces under tiles
- Wet areas
- Protection of various substrates in a wide range of applications..

#### PRODUCT INFORMATION

<b>Composition</b>	APP modified bitumen	
<b>Reinforcing material</b>	Non-woven polyester fabric	
<b>Packaging</b>	<b>Roll Size</b>	
	Length	10,00 m
	width	1,00 m
<b>Shelf life</b>	12 months from date of production	
<b>Storage conditions</b>	Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	

<b>Appearance and colour</b>	Top surface	Sand
	Backing	Polyethylene film
<b>Length</b>	10 m	
<b>Width</b>	1 m	
<b>Effective thickness</b>	3,0 mm ± 5 % (EN 1849-1)	

## TECHNICAL INFORMATION

<b>Resistance to impact</b>	≥ 600 mm at +23 °C (EN 12691- Method A)		
<b>Tensile strength</b>	Longitudinal	600 N/50 mm ± 20 %	(EN12311-1)
	Transversal	400 N/50 mm ± 20 %	
<b>Elongation</b>	Longitudinal	35% ± 20%	(EN12311-1)
	Transversal	45% ± 20 %	
<b>Tear strength</b>	Longitudinal	150 N ± 30 %	(EN 12310-1)
	Transversal	150 N ± 30 %	
<b>Joint shear resistance</b>	Longitudinal Min	500 N/50 mm	(EN 12317-1)
	Transversal Min	350 N/50 mm	
<b>Watertightness</b>	60 kPa (EN 1928-Method B)		

## APPLICATION INFORMATION

<b>Ambient air temperature</b>	+5 °C min. / +50 °C max.
<b>Relative air humidity</b>	80 % max
<b>Substrate temperature</b>	+5 °C min. / +50 °C max.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

- At low temperatures, take care while unrolling to avoid damaging the membrane.
- Use suitable footwear to avoid puncturing the membrane.
- Do not apply to wet, damp or unclean surfaces.
- Do not over-torch the membrane otherwise the polyester reinforcement (which melts at 260 °C) will be damaged making the membrane un-useable.
- If membrane is insufficiently heated, this can cause reduced adhesion to the substrate, between layers or on the overlaps.  
If this occurs, un-bonded areas must be lifted and re-torched.
- If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The supporting structure must be of sufficient structural strength to apply all new and existing layers of the waterproofing build-up. When used as a roofing membrane, the complete roof system must be designed and secured against wind uplift loadings. The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, dust and loosely adhering particles.

### SUBSTRATE PREPARATION

Use the appropriate preparation equipment to achieve the required substrate quality.

## APPLICATION METHOD / TOOLS

### Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions

### Priming

Apply the appropriate primer from Sika range, at the correct consumption to the prepared dry surface and allow to dry before next application stage. Refer to the individual Product Data Sheets.

### Alignment

Unroll, align and re-roll correctly before torching. Overlaps Side: 80 mm. End: 150 mm.

### Torching

Use a gas burner to heat the substrate and the backing film on the underside of membrane. When the backing film starts to melt, the membrane is ready to stick.

Roll the membrane forward and press firmly against the substrate to bond. Ensure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

### Detailing

All details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc. must be cut and sealed effectively. Detailing must follow the recommended guidelines and good practice for torch-applied membranes

### Protection

The membrane must be protected from damage during any ongoing site activities.

## MAINTENANCE

To maintain the function of the waterproofing during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing. Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc. including removing leaves, moss and other vegetation.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. SikaShield®

### Sika Egypt

1st Industrial Zone (A)  
Section #10, Block 13035  
El Obour City, Egypt  
TEL: +202 44810580  
FAX: +202 44810459  
egy.sika.com



### Product Data Sheet

SikaShield® P25 S EG 3 mm  
June 2022, Version 01.01  
020725101000000328

SikaShieldP25SEG3mm-en-EG-(06-2022)-1-1.pdf