



METHOD STATEMENT

Sikacrete[®] -114

DATE, : 06/2016

VERSION NO.01

SIKA EGYPT

ENG. ASHRAF ELZINY

TECHNICAL DEPARTMENT

Scope: Sikacrete[®] -114 is a one component, free-flowing, high strength, cement based micro-concrete with a maximum aggregate size of 10mm. Suitable for use in tropical and hot climatic conditions.

1. Preliminary Works and surface preparation

- 1.1 Concrete surfaces should be clean, sound and free from oil, grease, cement laitance and all loosely adhering particles.
- 1.2 Absorbent surfaces should be saturated thoroughly. Metal surfaces (iron and steel) should be free from scale, rust, oil and grease.

2. Mixing

- 2.1 Add 2.0 – 2.10 liter water for 20 kg powder
- 2.2 **Sikacretet[®] 114** must be mechanically mixed using a forced action mixer or in a clean drum using a drill and paddle (max. 500 rpm).



2.3 Mixing Tools



Collomix CK

3. Application

- 2.1 The minimum thickness is 50 mm. per pour (100 mm. for base plate grouting) & the maximum thickness is 500 mm. per pour.
- 2.2 The application of a suitable bonding agent, such as *Sikadur-32* or *SikaTop Armatec 110 EpoCem*, will improve adhesion on large areas or where particularly dense concrete substrates are involved.
- 2.2 Dampen the surface thoroughly with clean water prior to the application.
- 2.3 Before pouring, however, let the mixed grout stand for 2 - 3 minutes after mixing with water to allow entrapped air to escape.
- 2.4 Maintain sufficient hydrostatic head to keep the product flowing. Provide channels for the air to escape during grouting. Protect from rain until initial set has been achieved.

4. Curing

Treat exposed surfaces with *Antisol* Curing Compound or use other approved curing methods such as polyethylene sheeting or wet hessian. (Do not commence fogging until final set has been reached).

5. Notes:

- 4.1 Ensure formwork is secure and watertight to prevent movement and leaking during placing and curing.
- 4.2 At high temperatures use chilled water for mixing to keep grout temperature below 30°C.
- 4.3 In hot weather, base plates and foundations must be shaded from direct sunlight. Condition bags prior to use

For any further clarification don't hesitate to contact Sika Egypt Technical Department.

Technical Department

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Egypt
TECHNICAL DEPARTMENT

Version given by
Eng. Ashraf Elziny
Phone: 002-01223271730
Fax: 002-03-4244604
Mail: elziny.ashraf@eg.sika.com

Method Statement
Sikacrete® -114
DATE: : 07/2015, VERSION NO.01