

## PRODUCT DATA SHEET

# SikaShield® P26 MG EG 4 mm

Reinforced plastomeric bituminous waterproofing membrane torch applied, upper surface finish with mineral slated flakes

### DESCRIPTION

SikaShield® P26 MG EG 4 mm is a high performance plastomeric torch-on sheet waterproofing membrane. It is based on APP modified bitumen, reinforced with a 200 g/m<sup>2</sup> polyester non-woven fabric, faced with a layer of mineral slate flakes embedded on the top surface, to protect the membrane from UV radiation and ageing. Bottom side is faced with a polyethylene film. Suitable for use in tropical and hot climatic conditions.

### USES

SikaShield® P26 MG EG 4 mm may only be used by experienced professionals.

It is used as a waterproofing and roofing membrane for protection of various substrates in a wide range of application.

- Waterproofing and damp-proofing of basements against percolating water and damp soil
- Waterproofing of retaining walls and other concrete structures
- Waterproofing on flat roofs under protective layers or ballast
- UV exposed flat roofs Waterproofing on balconies, terraces and wetrooms under screed / tiles

### CHARACTERISTICS / ADVANTAGES

- Resistant to ageing
- Resistant to weathering and UV radiation
- Good tensile strength and elongation
- High resistance to water vapour
- Good dimensional stability
- Flexible at low temperatures
- Easy to install using the torch-on method
- Good resistance to mechanical impact

### PRODUCT INFORMATION

<b>Composition</b>	Atactic Polypropylene (APP) Modified Bitumen
<b>Packaging</b>	Roll size: 1 m (roll width) x 10 m (roll length)
<b>Shelf life</b>	12 months from date of production if stored properly in original unopened packaging.
<b>Storage conditions</b>	Rolls must be stored in their original package, in vertical position and under cool and dry conditions between temperatures of +5°C and +35°C. They must be protected from direct sunlight, rain, snow and ice.

<b>Appearance and colour</b>	Rolled sheet membrane, reinforced with polyester non-woven fabric 200 g/m <sup>2</sup> with mineral slate flakes embedded on the top surface and polyethylene film on the bottom side. Colour: grey, green, other colours on request		
<b>Length</b>	10.0 m (±1 %)		(EN 1848-1)
<b>Width</b>	1.0 m (±1 %)		(EN 1848-1)
<b>Effective thickness</b>	4 mm (±0.2 mm)		(EN 1849-1)
<b>Mass per area</b>	5.5 kg/m <sup>2</sup> (±10 %)		(EN 1849-1)
<b>Resistance to impact</b>	>700 mm		(EN 12691)
<b>Tensile strength</b>	Longitudinal	900 N/50 mm (±20 %)	(EN 12311-1)
	Transversal	600 N/50 mm (±20 %)	
<b>Elongation</b>	Longitudinal	40 % (-15)	(EN 12311-1)
	Transversal	45 % (-15)	
<b>Tear strength</b>	Longitudinal	≥550 N	(ASTM D5147 / D4037)
	Transversal	≥375 N	
<b>Joint shear resistance</b>	Longitudinal	≥500 N/50 mm	(EN 12317-1)
	Transversal	≥500 N/50 mm	
<b>Foldability at low temperature</b>	0 °C		(EN-1109)
<b>Watertightness</b>	Method A	≥ 60 kPa	(EN 1928-1)
	Method B	≥ 400 kPa	
<b>Ambient air temperature</b>	+5°C min. / +50°C max.		
<b>Substrate temperature</b>	+5°C min. / +65°C max.		

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Method Statement
- Application Guide / Manual
- To maintain the function of the waterproofing during its lifespan, it is advisable to arrange periodically for inspection of any exposed membrane and detailing. Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc. including removing leaves, moss and other vegetation

## IMPORTANT CONSIDERATIONS

- Do not apply to wet, damp or unclean surfaces.
- Do not over-torch the membrane otherwise the polyester reinforcement (which melts at +260 °C) will be damaged.
- If membrane is insufficiently heated, this can cause reduced adhesion to the substrate, between layers or on the overlaps. If this occurs, un-bonded areas must be lifted and re-torched.
- Avoid damage to previously installed

membranes during the torch-on of further layers of sheet membranes.

- Use suitable footwear to avoid puncturing the membrane.
- Watertightness testing of podiums, wet areas and roof structures is recommended after completion of the membrane installation works according to the specified project requirements.
- Flood testing maximum 48 hours at 50 mm depth. See ASTM D5957 for more information.
- Not resistant to root penetration

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data

## SUBSTRATE QUALITY

The supporting structure must be of sufficient structural strength to apply all new and existing layers of the waterproofing build-up. When used as a roofing membrane, the complete roof system must be designed and secured against wind uplift loadings. The substrate must be uniform, firm, smooth and

free of any sharp protrusion or burrs, clean, dry, free of grease, oil, dust and loosely adhering particles.

### SUBSTRATE PREPARATION

Use the appropriate preparation equipment to achieve the required substrate quality.

### APPLICATION METHOD / TOOLS

#### Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

#### Priming

Apply the appropriate primer from the Sika® Igoflex® or SikaBit® range, at the correct consumption to the prepared dry surface and allow to dry before next application stage. Refer to the individual Product Data Sheets.

#### Alignment

Unroll, align and re-roll correctly before torching.

#### Overlaps

Side: 100 mm. End: 150 mm.

#### Torching

Use a gas burner to heat the substrate and the backing film on the underside of membrane. When the backing film starts to melt, the membrane is ready to stick. Roll the membrane forward and press firmly against the substrate to bond. Ensure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying. Embossed membrane versions require less torching.

#### Detailing

All details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc. must be cut and sealed effectively. Detailing must follow the recommended guidelines and good practice for torch-applied membranes.

#### Protection

The membrane must be protected from damage during and after ongoing site activities, for example with Sikashield® Protection Sheet.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

#### Sika Egypt

1st Industrial Zone (A)  
Section #10, Block 13035  
El Obour City, Egypt  
TEL: +202 44810580  
FAX: +202 44810459  
egy.sika.com



#### Product Data Sheet

SikaShield® P26 MG EG 4 mm  
March 2023, Version 02.01  
020920011990001908