

## Sikament® -TG

### High Range Water Reducing Concrete Admixture

<b>Product Description</b>	Sikament® -TG is highly effective dual action liquid super plasticizer for the production of free flowing concrete or as a substantial water-reducing agent for promoting high early and ultimate strengths.  It complies with ASTM C-494 Type G and BS 5075 Part 3.
<b>Uses</b>	Sikament® -TG is used wherever high quality concrete is demanded under difficult placing and climatic conditions.
<b>Advantages</b>	Sikament® -TG provides the following properties:  <u>As a Super Plasticizer:</u> Substantial improvement in workability without increased water or the risk of segregation. Long lasting control of slump loss. No adverse effect on ultimate strengths.  <u>As a Water Reducer:</u> Early strengths significantly increased. High ultimate strengths. Up to 25% water reduction. Especially suitable for hot climates. No excessive air entrainment. No adverse Shrinkage effect. Improved surface finish. Increased water tightness.  Chloride-free-does not attack reinforcement.
<b>Technical Data</b>	
<b>Base</b>	Synthetic Type Dispersion
<b>Appearance / Colour</b>	Brown liquid
<b>Density (at 20°C)</b>	1.180 (ASTM C-494)
<b>Packaging</b>	5 and 20 kg pails 220 kg drums Bulk Tanks packing available upon request
<b>Storage</b>	Store in dry conditions, protected from direct sunlight and frost.
<b>Shelf Life</b>	12 months from date of production if stored properly in undamaged and unopened original sealed packing.
<b>Application</b>	
<b>Dosage</b>	0.6 - 2.5 % by weight of cement depending on desired workability and strength. Trial mixes shall be carried out for the determination of the suitable dosage.
<b>Dispensing</b>	Sikament® -TG can be added to the mixing water prior to its addition to the aggregates or directly to the freshly mixed concrete (the plasticizing effect is more pronounced).  For Ready-mix concrete, Sikament® -TG is added to the concrete immediately prior to discharge and after further mixing has taken place for three minutes.
<b>Important Notes</b>	Sikament® -TG is compatible with all types of Portland cement including S.R.C.
<b>Safety Instructions</b>	
<b>Safety Precautions</b>	Accidental splashes to the skin must be washed off with water and soap. Accidental splashes to the eyes or mucous membrane must be rinsed with clean warm water. Seek medical attention.
<b>Ecology</b>	Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.
<b>Transport</b>	Non-hazardous
<b>Toxicity</b>	Non-Toxic under relevant health and safety codes.



# Construction

## Legal notes

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



**Sika Egypt for Construction Chemicals**  
El Obour City  
1<sup>st</sup> industrial zone (A)  
Section # 10 Block 13035,  
Egypt

Tel :+202- 4481 0580  
Fax :+202- 4481 0459  
Mob :+20122- 2390 8822/55  
[www.sika.com.eg](http://www.sika.com.eg)

