# Sika<sup>®</sup> Unitherm<sup>®</sup> concrete S

Solvent based fire protection coating system

For concrete, interior use

Product Description	Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S is a solvent based fire protection coating system for concrete, masonry and brickwork located in interior situations, i.e.not exposed to weathering. Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S forms an insulating carbon char foam under the effect of heat or fire and protects the concrete substrate against heat and fire. Apply Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S on masonry or concrete areas to provide a fire resistance period up to 240 minutes according to prENV 13381-3.
Application areas:	For interior use on concrete, masonry and brickwork to improve the fire resistance.
Characteristics:	<ul> <li>Protection of concrete, masonry and brickwork against fire or heat</li> <li>Delays heat transfer through walls in case of fire</li> <li>Low material consumption</li> <li>Simple application</li> <li>Individual coloration possibe with corresponding topcoat, various colour shades in RAL, others available</li> </ul>

## **Product Data**

Colour shades:	White
Packaging	25 kg, net weight.
IMDG-Code No:	Class 3.3, UN-No.: 1263
Shelf-Life	12 months from date of production in coal and dry storage conditions, original, unopened containers.
Systems	
Coating systems:	<u>Fire protection coating for concrete;</u> Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S Topcoat
	Sika <sup>®</sup> Unitherm <sup>®</sup> 7854
Surface	Surfaces to be coated must be sweeped off and vacuum cleaned afterwards.
Pre-treatment:	The areas have to comply with building standards. They have to be solid, adherent, free of sludge, dirt, oil, grease, wax, water-repellent agents and other contamination preventing proper adhesion. Residual humidity in the concrete must be below 4% according to CM-humidity measuring instrument.
	A compatibility test on existent coatings with the fire protection system is recommended.
	Any damage (impact, corrosion, etc.) should be repaired prior the coating.
Technical Data	
Mass density:	Approx. 1.29 g/cm <sup>3</sup>
Solids by weight:	~ 70% (according: EN ISO 3251)
Flash point:	+ 26° C



Innovation & since Consistency 1910

#### Consumption:

#### Protection of concrete walls, masonry and brickwork

Fire resistance period (minutes)	Concrete thickness (mm)	Coverage (kg/m <sup>2</sup> )	
120	≥ 70	0.8	
180	≥ 87	0.8	
240	≥ 97	2.0	

Several coating layers are necessary for quantities of more than 800 g/m<sup>2</sup>

### **Application instructions**

Preparation of Coating material:	Stir thoroughly with slow turning mechanical stirrer, free of lumps.	
Application Method:	Airless spraying:         -       Material shall be applied undiluted         -       Airless spray equipment with transmission > 45 : 1, flow rate 4 -5 l/min.         -       Screens and filters must be removed         -       Hose diameter not below 3/8"         -       Whip line 1.5 -2 m, NW 6 may be used         -       Recommended nozzle size 0.53 – 0.66 mm or 0.019" - 0.027"         -       Solvent resistant hoses must be used!         Brushing / rolling:         -       Material shall be applied undiluted	
Application Conditions:	Object temperature not below +5°C, to max. +50°C Relative humidity max. 80% Application temperature shall be at least ≥ 3 K above dew point. In case relative humidity exceeds 80% special measures must be taken to prevent the condensation forming while application	
Drying;	Approx. 15 hours for each fire protection coat for exterior use at +20°C object temperature and 65% relative humidity. Lower temperature, higher relative humidity and different fire protection coating thickness may extend drying time. Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S requires a minimum of 48 hours drying before the application of topcoat Sika <sup>®</sup> Unitherm <sup>®</sup> 7854. Through-drying of Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S can be checked by "fingernil-test"	
Cleaning of equipment:	Immediately after use with Sika Unitherm thinner 11089.	
Important not	ice	
EU Regulation 2004/42 (Decopaint Directive)	The maximum allowed VOC content acc. To EU regulation 2004/42 (product class IIA / i, type Sb) in the ready for use material is 500 g/l (limit 2010). The maximum VOC content of Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S is < 500 g/l VOC.	

2004/42 (Decopaint	i, type Sb) in the ready for use material is 500 g/l (limit 2010).
Directive)	The maximum VOC content of Sika <sup>®</sup> Unitherm <sup>®</sup> concrete S is < 500 g/l VOC.
Notes regarding	Detailed health and safety information as well as relevant precautionary measures – e.g. physical, safety, toxicological and ecological data – may be found in our material safety data sheets.
hazards:	Please consider all relevant and applicable regulations regarding hazardous substances.
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Construction