Sikament® -G20

High Range Water Reducing and Retarding Concrete Admixture

	A bishbooties of a consequence of a consequence of the consequence of
Product	A highly effective super plasticizer with a slight set retarding effect for producing
Description	free-flowing concrete in hot climates. Also, a substantial water reducing agent for
-	promoting high early and ultimate strengths.
	Complies to: ASTM C-494 Type G and BS EN 5075 part 3.
Uses	Sikament® -G20 as a super plasticizer for flow concrete in :
	■ Floor slabs.
	Foundations.
	Slender components with packed reinforcement.
	■ Walls.
	Columns.
	Beams and ceilings.
Advantages	Sikament® -G20 provides the following properties :
	As a super plasticizer
	Substantial improvement in workability without increased water or the risk of
	segregation. Long lasting control of slump loss. No adverse effect on ultimate
	strengths.
	As a water reducer
	Early and ultimate strengths significantly increased. Up to 25% water reduction.
	Especially suitable for hot climates. No excessive air entrainment. No adverse
	shrinkage effect. Improved surface finish. Increased water tightness.
	Chloride Free (according to British Standards).
Technical Data	
Technical Data	Synthetic Dispersion.
Technical Data Type Colour	Synthetic Dispersion. Dark Brown.
Type Colour	Dark Brown.
Type Colour Density (at 20°C)	Dark Brown. 1.18 kg/l (ASTM C-494)
Type Colour Density (at 20°C) Storage Conditions	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost.
Type Colour Density (at 20°C) Storage Conditions Shelf life	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened.
Type Colour Density (at 20°C) Storage Conditions	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails
Type Colour Density (at 20°C) Storage Conditions Shelf life	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request)
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required.
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required. Sikament® -G20 although compatible with all types of Portland cement including
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required. Sikament® -G20 although compatible with all types of Portland cement including SRC, may perform differently with variations in cement producers and cement
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application Dosage	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required. Sikament® -G20 although compatible with all types of Portland cement including SRC, may perform differently with variations in cement producers and cement chemical composition.
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required. Sikament® -G20 although compatible with all types of Portland cement including SRC, may perform differently with variations in cement producers and cement chemical composition. Sikament® -G20 can be added separately to the freshly mixed concrete or directly
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application Dosage	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required. Sikament® -G20 although compatible with all types of Portland cement including SRC, may perform differently with variations in cement producers and cement chemical composition. Sikament® -G20 can be added separately to the freshly mixed concrete or directly to the mixing water prior to its addition to the aggregates.
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application Dosage	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required. Sikament® -G20 although compatible with all types of Portland cement including SRC, may perform differently with variations in cement producers and cement chemical composition. Sikament® -G20 can be added separately to the freshly mixed concrete or directly to the mixing water prior to its addition to the aggregates. When added separately to the freshly mixed concrete, further mixing should take
Type Colour Density (at 20°C) Storage Conditions Shelf life Packaging Application Dosage	Dark Brown. 1.18 kg/l (ASTM C-494) When possible protect from direct sunlight. Free from frost. 12 months when unopened. 5 Kg & 20 Kg pails 220 kg drums (Bulk Tanks are available upon request) The dosage of Sikament® -G20 will be between approximately 0.6% - 2.0 % by weight of cement, however, it is advisable to carry out trial mixes to establish the correct dosage rate required. Sikament® -G20 although compatible with all types of Portland cement including SRC, may perform differently with variations in cement producers and cement chemical composition. Sikament® -G20 can be added separately to the freshly mixed concrete or directly to the mixing water prior to its addition to the aggregates.



Safety Instructions	
Ecology	Contain and collect with absorbent materials and dispose of in accordance with current local or national regulations.
Transport	Non-hazardous.
Safety Precautions	Contains material, which may in certain cases cause skin irritation: Cleanliness is required.
	In case of skin contact, wash thoroughly with soap and water: In case of eye contact, flush with water for 15 minutes, contact a Physician: wash clothing before re-use.
Toxicity	Non-Toxic under relevant health and safety codes.
Legal notes	The information and in particular the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the technical data sheet for the product concerned, copies of which will be supplied on request. For further technical information, please consult our technical service department.



Sika Egypt for Construction Chemicals El Abour City 1st industrial zone (A) Section # 10 Block 13035, Egypt

Tel :+202- 4481 0580 Fax :+202- 4481 0459 Mob :+2012- 2390 8822/55 www.sika.com.eg

