

Method Statement for Application “SIKA EGYPT”

Sikadur -41CF

Scope: Epoxy Resin Patching Mortar

Preliminary Works and surface preparation

- 1.1 Clean out surfaces, using small wire brushes or compressed air to remove all loose and friable materials, as well as mud and other impurities.
- 1.2 All concrete surfaces must be clean, free from standing water and all loosely adhering particles.. Concrete must be full cured at least 3 - 6 weeks old, depending on climate.
- 1.3 Make sure the concrete has dried prior the application with Sikadur 41CF.

2. Execution

Mixing

- 2.1 Mix the resin material Sikadur 41CF according the instruction to use (see data-sheet) recommended mechanical mixing with electrical stirrer (300-500 rpm) and using the correct sika mixing paddle (disc type) and apply only while the material is in its Pot life time (approx. 60 minutes at 30 Deg. Celsius).



Mixing Tools




Drill and Mixing Paddle
Small quantities



Double Mixing Paddle
Medium quantities

Application

- 2.2 Primer is required, on damp concrete surfaces, where the use of Comp. A+B of the mortar as primer is recommended.
- 2.3 Apply directly to the prepared substrate by spatula, trowel or glove protected hand, depending on application.
- 2.3 Maximum thickness per coat: 6 cm.
- 2.4 Average consumption 1 m²: approx. 2 kg (1 mm thickness).



When the repair depth exceeds the maximum layer thickness of the repair material, then layers may be built up on top of one another to increase the overall construction depth. The first layer shall be hardened and exothermic reaction of the material completed. The 1st layer shall be at ambient temperature before applying the second layer.

For any further clarification don't hesitate to contact Sika Egypt Technical Department.

Sika Egypt Technical Department

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request



Sika Egypt El About City 1st industrial zone (A) Section # 10 Block 13035,
Phone: +2 02 6100714 / Fax: +2 02 6100759
Mobil : 0123271730