



METHOD STATEMENT

Sika Bitucoat[®] M

DATE, : 08 / 2015

VERSION NO. 1



SIKA EGYPT

ENG. ASHRAF ELZINY


TECHNICAL DEPARTMENT

Scope : Method Statement for Application of Emulsion containing rubber bituminous Coating for concrete **Sika Bitucoat® M.**


2. Surface preparation:

-  The good surface preparation is the base for Sika materials success.
-  Exposed Concrete without existing coating :
 - The substrate must be clean, dry and free from all traces of loose particles, laitance, oil, grease.
 - Concrete Substrate: Should be dry, clean and free from loose particles.
 - Suitable preparation methods are steam cleaning. High pressure water jetting or blast cleaning.

3. Mixing:

-  **Sika Bitucoat® M** is supplied ready for use .Stir thoroughly prior to application.


4. Application:

-  **Application method:**
 - Apply **Sika Bitucoat® M** as a primer evenly onto the substrate diluted with 5 – 10% water.
 - Top coat should be applied after drying the first coat.

5. Consumption:

system	Per Coat
First coat	0.35 – 0.40 Kg /m2
Second coat	0.15 – 0.20 Kg/m2



6. Cleaning:

-  Clean all tools and equipment immediately after use soap and water or Thinner 2.

7. Remarks:

-  **Waiting time / Overcoat ability :**

Previous coating	Waiting time	Next coating
Sika Bitucoat® M	2 hours min.	Sika Bitucoat® M

-  Sika Bitucoat® M doesn't require any special curing but must be protected from rain for at least 4 hour at +20°C.
-  Full curing 7 days.

For any further clarification don't hesitate to contact Sika Egypt Technical Department.

Technical Department

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request

SIKA EGYPT
TECHNICAL DEPETEMET

Version given by
Eng. Ashraf Elziny
Phone: 002-01223271730
Fax: 002-03-4244604
Mail: elziny.ashraf@eg.sika.com

Method Statement
Sika Bitucoat® M
DATE, : 07 / 2015, VERSION NO. 1

Language/Region/Translation template
TECHNICAL DEPETEMET