

PRODUCT DATA SHEET

Sikafloor®-91

A THREE-COMPONENT SOLVENT-FREE PIGMENTED MORTAR SCREED BASED ON EPOXY RESINS.

DESCRIPTION

A three-component solvent-free pigmented mortar screed based on epoxy resins.

USES

Sikafloor®-91 may only be used by experienced professionals.

As a non-slip, abrasion-resistant epoxy resin floorings of 5-8 mm thickness:

- Industrial floorings subject to moderate or heavy loading
- Workshop and factory floors
- Machine shops and warehouses
- Depots and loading ramps
- Hangars
- Stairs
- Suitable for use on ventilated or non ventilated substrates such as:
- Concrete and mortar.

CHARACTERISTICS / ADVANTAGES

- Easy and fast to apply.
- Solvent-free, no fire risk.
- Excellent adhesion to substrate.
- With the addition of Sikadur® -507 trowelling aid, the screed may be mechanically smoothed using a plastic coated disk.
- Non-slip, non-skid finish.
- Excellent abrasion resistance.
- High mechanical strength.
- Permeable to water vapour.

APPROVALS / CERTIFICATES

Sikafloor -91 has been tested as per SCAQMD Rule 304-91.

Result: VOC Content <100 g/L

PRODUCT INFORMATION

Composition	Epoxy
Packaging	Comp. (A+B): 3 kg Unit. Comp. C (Sikadur 506 EG): 30kg Bag.
Appearance / Colour	Natural, light grey, yellow oxide, red oxide, chrome oxide green. Other colours available on request (minimum order 300 kg)..
Shelf life	12 months from date of production if stored properly in original unopened packing. Note: Component (A), Sikafloor® -9l pigmented, must be thoroughly stirred with a mechanical stirrer prior to each batching. Segregation may occur after 10 hours.
Storage conditions	Store in dry condition at temperature between +5°C and +30°C
Density	2.1 - 2.2 kg/litre for finished screed

TECHNICAL INFORMATION

Compressive Strength	60 - 70 N/mm ²
Tensile Strength	6 - 8 N/mm ²
Tensile Adhesion Strength	> 1.5 N/mm ² (Concrete Failure)

SYSTEMS

Systems	Coating System 1. Priming coat: Sikafloor® -94 (Comp A+B) OR Sikafloor® -94 (Thixotropic) 2. Mortar screed: Sikafloor® -91 (Comp A+B+C) 5 - 8 mm applied thickness 2-Coverage: 0.2 - 0.3 kg/m ² (depending on condition of substrate) 0.3 - 0.4 kg/m ² (depending on condition of substrate) 11 - 18 kg/m ²
----------------	---

APPLICATION INFORMATION

Mixing Ratio	Sikafloor® -91 Flooring Screed: 1:10 mix Comp. (A), natural or pigmented 2.54 Comp. (B) 0.46 Comp. (C) (Sikadur506 EG) Parts by wt. 30
Substrate Temperature	Minimum substrate temperature: + 8C Maximum substrate temperature: + 30C Substrate temperature must be 3C above measured dew-point
Substrate Moisture Content	<4%
Pot Life	10°C 20°C 30°C 60 min. 45 min. 20 min.

Curing Time	10oC	20oC	30oC
Can be walked on after:	36 hrs.	24 hrs.	12 hrs.
Light mechanical loading possible after:	3 days	2 days	2 days
Fully cured after:	10 days	7 days	5 days

APPLICATION INSTRUCTIONS

MIXING

Stir Component (A) thoroughly with an electric stirrer prior to batching. Add Component (B) in the correct mix ratio and mix for 2-3 minutes at a low speed. Place the correctly batched quantity of Component (C) in the mixer (forced action type). Add the prepared resin mix (Components A+B) while the mixer is running, and continue to mix until a homogeneous and uniformly moist mix is obtained.

APPLICATION

Place the mortar while the primer coat is still tacky, and rake out evenly. Level with a beam laid across steel screeding rails and finish with a steel float.

CLEANING OF EQUIPMENT

- Clean all tools and equipment immediately after use with Colma Cleaner.
- Once hardened, the material can only be removed mechanically.
- Wash soiled hands and skin thoroughly in hot soapy water.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

This product can cause skin irritations in persons with sensitive skin.
Always rub barrier cream into hands and exposed skin before starting work.
Wear protective clothing (gloves and goggles). If Sika-floor® -91 is accidentally splashed into the eyes, nose, mouth or throat, flush immediately with plenty of clean, warm water and seek medical attention without delay.

LEGAL NOTES

The information, and, in particular, the recommenda-

tions relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

Sika Egypt

1st Industrial Zone (A)
Section #10, Block 13035
El Obour City, Egypt
TEL: +202 44810580
FAX: +202 44810459
egy.sika.com

Alexandria Office

4, Mihamed Masoud st
Bab Sharki
Alexandria
Tel: +203 4244 601/2/3
Mob:+2012-23909922
Fax: +203 4244 604

Cairo Sales office

222,El-Hegaz St, Heliopolis,
Cairo
Egypt
Tel:+202-26235032 /4
Mob:+2012-23999700
Fax:+202-26235637

Borg El-Arab Factory

2nd industrial zone block 28
Borg El Arab City, Alexandria
Egypt
Tel:+203-4592654/1417
Mob:+2012-23919291
Fax:+203-4592036



Product Data Sheet
Sikafloor®-91
May 2016, Version 01.01
020811020010000001

Sikafloor-91-en-EG-(05-2016)-1-1.pdf

